



ECOREL[™] FREE 300-31A

TIN/SILVER LEAD FREE ALLOY SOLDER PASTE
NO CLEAN SMT PRINTING PROCESS
EXCELLENT LOW VOIDING FOR DCB

BENEFITS

ECOREL FREE 300-31A is a no clean halogen-free lead-free solder paste developed with the reliable chemistry of the ECOREL range. It is designed to minimize flux spattering, solder leaking and voiding to achieve consistent bond-line thickness (BLT) between the large chips and the DCB substrate.

PERFORMANCE	 Low voiding to achieve consistent bond line thickness Very good wetting on copper surfaces Low post-reflow residues
COST	 Minimized copper oxidation for higher first-pass yield Minimized risks for wirebonding defects
HSE	No HalogenLead Free

FEATURES

FEATURES	ECOREL FREE 300-31A
Alloy	Sn96,5Ag3.5
Melting point (°C/°F)	221 / 426
Metal content (%)	89 +/- 0,5
Post reflow residues	Approximately 5% by w/w
Halogen content	No Halogen
Powder size	25 - 45 microns / Type 3
Spiral pump* Viscosity (Pa.s 25°C)	Typical 145

^{*}The equipment used to test spiral pump viscosity is Malcom at a 10 rpm rotation speed.

CHARACTERISTICS

CHARACTERISTICS	VALUES	
Flux Classification	ROL0	ANSI/J-STD-004B
Flux Classification	113	ISO 9454
Solder balling test	Pass	ANSI/J-STD-005A
Copper mirror	Pass	ANSI/J-STD-004B
Copper corrosion	Pass	ANSI/J-STD-004B
SIR (IPC)	Pass	ANSI/J-STD-004B
Electromigration (IPC)	Pass	ANSI/J-STD-004B
Bono Corrosion test (85°C / 85% HR – 15 days)	Pass Corrosion Factor <8%	Inventec procedure

PROCESS RECOMMENDATION

The best process will depend on factors such as operating conditions, equipment, board or component design. Our team is ready to advise you.

SOLDER PASTE PREPARATION

- Put the paste at room temperature for at least 4 hours prior to use.
- Before printing, it is essential to properly mix the solder paste, either manually with a spatula or by doing several
 preliminary prints on the stencil.
- Automatic solder paste mixing is neither required nor advised.

PRINTING GUIDELINE

Apply the solder paste to the stencil to form a roll of 1 to 2 cm in diameter all along the squeegee or around 100g per 10 cm of squeegee length. This way, the solder paste will roll easily under the squeegees to offer excellent printing quality.

PARAMETER	REMARK	
Printing speed	Minimum 20 to maximum 150 mm/s (1 to 6 inch/s) Maximum depends on printer capabilities	
Minimum pitch	0.4 mm for Type 3 powder	
Pressure	Guideline value for a 250 mm squeegee is 7 Kg at 100 mm/s Actual value depends on equipment, printing speed and squeegee length	
Stencil life in continuous printing process	>12 hours	
Abandon time between prints	>4 hours	
Steady tackiness	>16 hours	

REFLOW GUIDELINE

Soldering DCB modules requires specific conditions to minimize voids level while achieving consistent BLT. This step usually requires specific thermal profiles with vacuum, adjusted in accordance with the type of ovens, modules and components involved: batch conduction oven with vacuum is the preferred option.

Alternative options are vapor phase oven with vacuum (lower peak temperature and shorter time above liquidus) or convection oven with vacuum.

CLEANING POST SOLDERING

ECOREL FREE 300-31A is a no-clean solder paste, so cleaning is not required to meet IPC standards. The chemistry is specially designed so that any remaining flux residue is chemically inert and will not impact your assembled board or packaging under normal conditions. However, when cleaning is desired or required (e.g. high reliability assembly or to improved conformal coating adhesion), the flux residue can be easily removed with INVENTEC's own formulated flux cleaners.

Inventec has more than 40 years experience in high-tech cleaning for aqueous and solvent based systems.

Our solder materials are aligned with our cleaning solutions, providing you a guaranteed cleaning result with our materials.

PROCESS TYPE	PCBA DEFLUXING SOLUTIONS
Manual	Topklean TM EL10F / Topklean TM EL60 / Quicksolv TM DEF90
Aqueous system (Immersion or spray)	Promoclean™ DISPER 707 / DISPER 607 / TP 1113
Co-solvent system	Topklean [™] EL 20P or EL 20A + HFE bases solvents
Mono-solvent (Azeotropic)	Promosolv [™] 70ES

Other products available, depending on specific customer requirements. Check also our maintenance cleaning solutions.



ECOREL™ FREE 300-31A

PACKAGING, STORAGE & SHELF LIFE

- To ensure the best product performance, the recommended storage temperature range is from 0°C to 10°C.
- For an optimal preservation, store cartridges in a vertical position, tip downwards.
- Shelf-life is 12 months for jar packaging & 9 months for cartridges

AVAILABLE PACKAGING





JAR 500g

CARTRIDGE 600g

HEALTH, SAFETY & ENVIRONMENT

No issues when used as recommended.

In accordance with the Annex II of Directive 2011/65/UE (RoHS), including its amendments, we certify that this product does not contains quantities above 0.1% of Hg, Pb, Cr VI, PBB, PBDE, DEHP, BBP, DBP, DIBP and above 0.01% of Cd. . INVENTEC PERFORMANCE CHEMICALS also fulfils its direct obligations under the REACH and Conflict Mineral regulations.

Please refer always to the Safety Data Sheet (SDS or MSDS) prior to use. Our SDS can be downloaded at <u>www.quickfds.com</u>. We will request to provide your email address, so we can automatically send you a new version of the SDS when a future update would occur.



ECOREL™ FREE 300-31A PDS2021-03 ENv1

TECHNICAL SUPPORT & FREE-OF-CHARGE TESTING

Inventec has a worldwide dedicated Technical Support team to help you along the different stages of our cooperation.

Depending on your request, we provide online or onsite support

- to select the right product based on your specific needs
- to assist you in your product qualification process
- to guide you with the initial set up of you process at all your worldwide manufacturing facilities
- to provide fast response on technical issues which could occur at any time during mass production.

When prior cleaning is required, customers are also welcome in our CLEANING CENTERS to see the process in action and to get convinced by our solutions. We cover water- and solvent based processes.

Inventec is unique in the world by developing not only soldering materials but also cleaning and coating solutions. These materials are very closely linked with each other from a process point of view. Talking to our Technical Team, who understands very well these 3 different product groups, will help you greatly to overcome technical challenges within your overall process.

Contact our technical support via contact@inventec.dehon.com or your local sales representative.

ABOUT INVENTEC

Inventec is a global provider of SOLDERING, CLEANING & COATING materials for Electronic, Semiconductor and Industrial applications. For over 40 years we have shown leadership in innovation by putting HEALTH IMPACT, SUSTAINABILITY and RELIABILITY at the core of our product development.

With ISO 9001 & 14001 production sites in France, Switzerland, USA, Mexico, Malaysia and China we can guarantee a smooth and cost-effective supply chain.

We supply to many industries but the excellent performance of our products in applications which demand high reliability, leads us to focus especially on the AUTOMOTIVE, AEROSPACE, SEMICONDUCTOR, ENERGY and MEDICAL industry.

www.inventec.dehon.com



SOLDERING • CLEANING • COATING

This data is based on information that the manufacturer believes to be reliable and offered in good faith. In no event will INVENTEC PERFORMANCE CHEMICALS be responsible for special, incidental and consequential damages. The user is responsible to the Administrative Authorities (regulations for the protection of the Environment) for the conformity of his installation.

Inventec Performance Chemicals – 26 rue de Coulons. 94360 Bry-sur-Marne, France Limited company with capital of 600 000€ - 964 500 706 RCS Créteil

