

NO CLEAN TACKY FLUX
LEADED/LEAD-FREE SOLDERING
EXCELLENT WETTING PROPERTIES

PRODUCT APPLICATION & HIGHLIGHTS

AMTECH™ 4300/LF-4300-TF is formulated for syringe, stencil printing, and rework applications on all PCB surface finishes. **AMTECH 4300/LF-4300-TF** may be used for BGA sphere attachment and reballing. This tacky flux is also designed to work on all flip chip bumping and chip scale packaging sites.

- RELO flux classification
- Wide process window
- Excellent wetting compatibility on most board finishes
- Low voiding, including LGA
- REACH compliant
- Optimized for Lead-free and standard alloy systems

COMPATIBLE ALLOYS

ALLOY	TEMPERATURE °C	TEMPERATURE °F
63Sn/37Pb	183	361
62Sn/36Pb/2Ag	179	354
42Sn/58Bi	138	280
96.5Sn/3.0Ag/0.5Cu	217-220	423-428
99.0Sn/0.3Ag/0.7Cu	217-221	423-430
96.5Sn/3.5Ag	221	430
95Sn/5Sb	235-240	455-464
95Sn/5Ag	221-245	430-473

Custom alloys available on request.

TEST RESULTS



TEST J-STD-004 OR OTHER REQUIREMENTS (AS STATED)	TEST REQUIREMENT	RESULT
Copper Mirror	IPC-TM-650: 2.3.32	L: No breakthrough
Corrosion	IPC-TM-650: 2.6.15	L: No corrosion
Quantitative Halides	IPC-TM-650: 2.3.28.1	L: <0.5%
Electrochemical Migration	IPC-TM-650: 2.6.14.1	L: <1 decade drop (no clean)
Surface Insulation Resistance 85°C, 85% RH@ 168 Hours	IPC-TM-650: 2.6.3.3	L: 100 MΩ (No-clean)
Viscosity Malcom @ 10 RPM/25°C (x103mPa/s)	IPC-TM-650: 2.4.34.4	20-48
Visual	IPC-TM-650: 3.4.2.5	Clear and free from precipitation
Conflict Minerals Compliance	Electronic Industry Citizenship Coalition (EICC)	Compliant
REACH Compliance	Articles 33 and 67 of regulation (EC) No 1907/2006	Contains no substance >0.1% w/w that is listed as a SVHC or restricted for use in solder materials

PROCESS RECOMMENDATION

The best process will depend on factors such as operating conditions, equipment, board or component design. Our team is ready to advise you.

REFLOW GUIDELINE

This profile is designed to serve as a starting point for process optimization. To achieve better results with voiding or to reduce tombstoning, consider using a longer soaking zone, for 60-90 seconds, with a rapid pre-heat stage. If there is evidence of solder de-wetting, consider lowering the peak reflow temperature, or reduce the time above liquidus to <90 seconds.



CLEANING POST SOLDERING

This product is a no-clean solder paste, so cleaning is not required to meet IPC standards. The chemistry is specially designed so that any remaining flux residue is chemically inert and will not impact your assembled board or packaging under normal conditions. However, when cleaning is desired or required (e.g. high reliability assembly or to improved conformal coating adhesion), the flux residue can be easily removed with INVENTEC's own formulated flux cleaners.

Inventec has over 60 years' experience in high-tech cleaning for aqueous and solvent based systems. Our solder materials are aligned with our cleaning solutions, which guarantees excellent cleaning with our materials.

PROCESS TYPE	DEFLUXING SOLUTIONS
Manual	Quicksolv™ DEF90, Quicksolv™ DEF70, Promoclean™ TP61
Aqueous (Immersion or spray)	Promoclean™ DISPER 607, Promoclean™ DISPER 707, Promoclean™ DISPER 800
Co-solvent	Topklean™ EL 80 + Promosolv™ rinsing solvents
Mono-solvent (vapor phase)	Promosolv™ 70ES, Promosolv™ 70IS

Other products available, depending on specific customer requirements. Check also our maintenance cleaning solutions.

PACKAGING, STORAGE & SHELF LIFE

- To ensure the best product performance, the recommended storage temperature is at room temperature (20°C to 25°C).
- For an optimal preservation, store cartridges & syringes in a vertical position, tip downwards.
- Shelf-life is 12 months when properly stored

AVAILABLE PACKAGING



JAR
75g & 150g



CARTRIDGE
170g & 340g



SYRINGE
10cc / 30cc

HEALTH, SAFETY & ENVIRONMENT

No issues when used as recommended. In accordance with the Annex II of Directive 2011/65/UE (RoHS), including its amendments, we certify that this product does not contains quantities above 0.1% of Hg, Pb, Cr VI, PBB, PBDE, DEHP, BBP, DBP, DIBP and above 0.01% of Cd. INVENTEC PERFORMANCE CHEMICALS also fulfills its direct obligations under the REACH and Conflict Mineral regulations. Please refer always to the Safety Data Sheet (SDS or MSDS) prior to use. Our SDS can be downloaded at www.quickfds.com. We will request to provide your email address, so we can automatically send you a new version of the SDS when a future update would occur.

TECHNICAL SUPPORT & FREE-OF-CHARGE TESTING

Inventec has a worldwide dedicated Technical Support team to help you along the various stages of our cooperation.

Depending on your request, we provide online or onsite support:

- To select the right product based on your specific needs
- To assist you in your product qualification process
- To guide you with the initial set up of your process at all your worldwide manufacturing facilities
- To provide fast response on technical issues which could occur at any time during mass production

When flux cleaning is necessary, customers are welcome to visit our CLEANING CENTERS to witness the process firsthand and experience the effectiveness of our solutions. We offer both aqueous- and solvent-based processes.

Inventec is unique in the world by developing not only cleaning materials but also soldering and coating solutions. These materials are very closely linked with each other from a process point of view. Talking to our Technical Team, who understands very well these 3 different product groups, will help you greatly to overcome technical challenges within your overall process.

Contact our technical support via contact@inventec.dehon.com or your local sales representative.

ABOUT INVENTEC & AMTECH

Inventec™ is a global provider of **SOLDERING, CLEANING, COATING, COOLING** materials for **Electronic, Semiconductor and Industrial applications**. For over 60 years we have shown leadership in innovation by putting **HEALTH IMPACT, SUSTAINABILITY** and **RELIABILITY** at the core of our product development.

With ISO 9001 & 14001 production sites in France, Switzerland, USA, Mexico, Malaysia and China we can guarantee a smooth and cost-effective supply chain.

We supply to many industries but the excellent performance of our products in applications which demand high reliability, leads us to focus especially on the **AUTOMOTIVE, AEROSPACE, SEMICONDUCTOR, ENERGY** and **MEDICAL** industry.

Inventec™ acquired **AMTECH™** in 2014, from where it received the rights to manufacture and commercialize the **AMTECH™** product range. **Inventec™** will remain supplying **AMTECH™** products to our worldwide customers by aligning to our **Inventec™** branding policy. If you are in doubt that you are buying genuine **AMTECH™** product, contact us to check if your supply source is an authorized distributor or reseller. **AMTECH™** products are produced in the USA.



<http://>

www.inventec.dehon.com
www.shop.inventec.dehon.com
www.inventecusa.com



SOLDERING

CLEANING

COATING

COOLING

This data is based on information that the manufacturer believes to be reliable and offered in good faith. In no event will INVENTEC PERFORMANCE CHEMICALS be responsible for special, incidental and consequential damages. The user is responsible to the Administrative Authorities (regulations for the protection of the Environment) for the conformity of his installation.

Inventec Performance Chemicals USA – 500 Main Street, Suite 18, PO Box 989, Deep River, CT 06417 USA

Toll Free: 800.435.0317 – Phone: 860.526.8300 – Fax: 860.526.8242

Inventec Performance Chemicals – 26 rue de Coulons. 94360 Bry-sur-Marne, France

Limited company with capital of 600 000€ - 964 500 706 RCS Créteil